


Performance of MEGTRON6 with H-VLP

1) Transmission Loss

MEW Confidential



2) Peel Strength [kN/m]

	12 μ m	18 μ m	35 μ m
H-VLP	0.5 (0.9)	0.55 (0.85)	0.8 =0.02
S-VLP	-	-	0.8 =0.07
VLP	0.6	0.7	-
Conventional	0.9	1.1	1.2

* () ... as 35um copper with plating totally

3) Oven Heat resistance []

	12 μ m	18 μ m	35 μ m
H-VLP	280	280	280
S-VLP	-	-	260
VLP	270	270	-
Conventional	270	270	270