

# PEWEMT – R1551LW (Low flow) Data Sheet

Product	Glass Style	Type	Resin Content (%)	Resin Flow (mm)	Volatile Content (%)	Scaled Flow (mil)	* Calculate Thickness ( $\mu\text{m}$ ) (C/F Residue 100%)
R1551LW (Low Flow)	2116	MF	57 $\pm$ 3	0.1 ~ 1.5	< 1.5	5.2 $\pm$ 0.4	130
	1080	SF	71 $\pm$ 3	0.1 ~ 1.5	< 1.5	3.7 $\pm$ 0.4	95
		MF	63 $\pm$ 3	0.1 ~ 1.5	< 1.5	2.9 $\pm$ 0.4	70
	106	SF	78 $\pm$ 3	0.1 ~ 1.5	< 1.5	2.6 $\pm$ 0.4	67
		HF	76 $\pm$ 3	0.1 ~ 1.5	< 1.5	2.5 $\pm$ 0.4	60
		MF	73 $\pm$ 3	0.1 ~ 1.5	< 1.5	2.2 $\pm$ 0.4	53
	1067	HF	75 $\pm$ 3	0.1 ~ 1.5	< 1.5	2.8 $\pm$ 0.4	73
		MF	73 $\pm$ 3	0.1 ~ 1.5	< 1.5	2.7 $\pm$ 0.4	67
		LF	71 $\pm$ 3	0.1 ~ 1.5	< 1.5	2.5 $\pm$ 0.4	60
		FF	69 $\pm$ 3	0.1 ~ 1.5	< 1.5	2.3 $\pm$ 0.4	57
	1037	MF	70 $\pm$ 3	0.1 ~ 1.5	< 1.5	1.8 $\pm$ 0.4	45
		LF	68 $\pm$ 3	0.1 ~ 1.5	< 1.5	1.8 $\pm$ 0.4	40

\* Calculate Thickness data is the reference value not the assured value.